

Medium power lithium-ion cells

VL M cells

Saft VL M cells combine the benefits of high power lithium electrode technology with enhanced energy density. This cell is proposed in Saft modules or customized battery system constructions.

Saft's battery system

Individual lithium-ion cells need to be mechanically and electrically integrated into battery systems to operate properly. The battery system include electronic devices for performance, thermal and safety management specific to each application.

Features

- High specific energy and power
- Excellent cycle and calendar life
- Maintenance free
- Fast continuous charge capability 1C rate

Applications

- Electric and hybrid vehicles
- Telecommunication networks
- Stationary
- Space and Defence
- Any application requiring an optimal balance between high power and high energy

Technology

- Graphite-based anode
- Nickel oxide-based cathode
- Electrolyte: blend of carbonate solvents + LiPF₆



VL 41M	
Electrical characteristics	
Nominal voltage (V)	3,6
Average capacity C/3 after charge to 4.0 V/cell (Ah)	41
Minimum capacity C/3 after charge to 4.0 V/cell (Ah)	39
Specific energy after charge to 4.0 V/cell (Wh/kg)	136
Energy density after charge to 4.0 V/cell (Wh/dm ³)	285
Specific power (30s peak 50% DOD) (W/kg)	794
Power density (30s peak 50% DOD) (W/dm ³)	1667
Mechanical characteristics	
Diameter (mm)	54.3
Height (mm)	222
Typical weight (kg)	1.07
Volume (dm ³)	0.51
Voltage limits	
Charge (V)	4.0 (4.1 for peak)
Discharge (V)	2.7 (2.3 for peak)
Current limits	
Max continuous current (A)	150
Max peak current during 30 s (A)	300




saft


Medium power Li-ion

VL 41 M cell


Cell capacity and voltage according to current at +20°C



Power during 30 s at 300 A discharge pulse at +20°C



Cycling life in DST profil at 80% of DOD at +20°C. Energy in discharge at C/3 rate and power 30s at 250 A at 50% of S.O.C.



Saft
Communication Department
 12, rue Sadi Carnot
 93170 Bagnolet - France
 Phone: +33 (0)1 49 93 19 18
 Fax: +33 (0)1 49 93 19 68

www.saftbatteries.com

DOC N° 54042-2-0305
 Edition: March 2005

Data in this document are subject to change without notice and become contractual only after written confirmation by Saft.

Photo credit: Studioland

Société anonyme au capital de 31 944 000 €
 RCS Bobigny B 383 703 873

Prepared by PACIFIC & co.



SAFT